

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 February 2002 (14.02.2002)

PCT

(10) International Publication Number
WO 02/012144 A3

(51) International Patent Classification⁷: **C04B 26/04**,
E04F 13/00, C04B 41/61 // (C04B 26/04, 14:04, 14:10,
14:18, 14:28, 24:38)

(74) Agent: **CABINET HIRSCH**; Groupement N° 161, 34, rue
de Bassano, F-75008 Paris (FR).

(21) International Application Number: **PCT/EP01/09336**

(22) International Filing Date: **31 July 2001 (31.07.2001)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA,
ZW.

(30) Priority Data:
09/633,264 4 August 2000 (04.08.2000) **US**

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).

(71) Applicant (*for all designated States except US*): **LA-
FARGE PLATRES** [FR/FR]; 500, rue Marcel Demonque,
Zône du Pôle Technologique - Agroparc, F-84915 Avignon
Cedex (FR).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **ZUBER, François**
[FR/FR]; Villa Les-Deux-Pins, Colline Saint-Anne,
F-84270 Vedère (FR). **LECLERCQ, Claude** [FR/FR];
Chemin des Coudoulets, F-84800 Pernes-les-Fontaines
(FR). **BOURNE-CHASTEL, Pascal** [FR/FR]; Rue Le
Cours, F-84570 Mormoiron (FR). **COLBERT, Eliza-
beth, A.** [US/US]; 1461 Oxbow Drive, Blacklick, OH
43004 (US). **GAGNE, Pierre** [CA/CA]; 2572 Beaumont,
Varennes, Quebec J3X 1K1 (CA). **BOUCHER, Roland**
[CA/CA]; 1176 Rue Girard, St-Hubert, Quebec J4T
1H4 (CA). **BILODEAU, Sylvie** [CA/CA]; 219 Chemin
St-Armand, St-Armand, Quebec J0J 1T0 (CA).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

(88) Date of publication of the international search report:
6 September 2002

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

WO 02/012144 A3

(54) Title: **METHOD, ASSEMBLY AND ADDITIONAL COAT FOR THE CONSTRUCTION OF INTERIOR WORKS**

(57) Abstract: The present invention provides a construction assembly for interior works, comprising: prefabricated elements, e.g. gypsum fiberboards, wherein said prefabricated elements comprise a coating layer formed of at least one skim coat deposited on said prefabricated elements; and at least one jointing material, e.g. a sealing coat, which joints adjacent said prefabricated elements to form a substantially plane outer surface comprising the visible surface of said at least one jointing material and the visible surface of the skim coated prefabricated elements, wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the composition of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one skim coat are adapted to each other, whereby said at least one jointing material and said skim coat form, both in a dry state, a substantially homogeneous surface and whereby said outer surface is ready to be decorated.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/09336

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C04B26/04 E04F13/00 C04B41/61 //(C04B26/04,14:04,14:10,
 14:18,14:28,24:38)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B E04F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	US 6 105 325 A (BOURNE-CHASTEL PASCAL ET AL) 22 August 2000 (2000-08-22)	1,2,9, 10,12, 13,19, 20,27, 28,30, 31,37, 38,45, 46,48, 49,55, 59,60, 62,63
Y	column 4, line 30-34; claims 1,3,5,6,9,11,13,16,17,19,20,32	7,8,25, 26,43, 44,57,58
	---	-/--



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

10 May 2002

Date of mailing of the international search report

22/05/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Daeleman, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/09336

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 454 267 A (WILLIAMS TERRANCE L) 12 June 1984 (1984-06-12) claims 1,6,9,11	7,8,25, 26,43, 44,57,58
A	FR 2 736 079 A (PLATRES LAFARGE) 3 January 1997 (1997-01-03) claims	1-67
X	EP 0 521 804 A (LAFARGE PLATRES) 7 January 1993 (1993-01-07) cited in the application the whole document	55-67
X	DE 37 21 668 A (MUANYAGIPARI KUTATO INTEZET ;SZENT FOEVAROSI EPITOEIPARI VA (HU)) 5 January 1989 (1989-01-05) claim 1	55
X	CHEMICAL ABSTRACTS, vol. 103, no. 8, 26 August 1985 (1985-08-26) Columbus, Ohio, US; abstract no. 58270z, page 278; XP000185205 abstract & JP 60 065197 A (SAN ROKKU KOGYO K K) 13 April 1985 (1985-04-13)	55
A	DATABASE WPI Week 199727 Derwent Publications Ltd., London, GB; AN 1997-293470 XP002198594 & JP 09 109131 A (MITSUBISHI MATERIALS) abstract	5,23,41, 67

INTERNATIONAL SEARCH REPORT
Information on patent family members

International Application No
PCT/EP 01/09336

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6105325	A	22-08-2000	FR 2736079 A1	03-01-1997
			AU 719427 B2	11-05-2000
			AU 6013696 A	05-02-1997
			BR 9606456 A	14-07-1998
			CA 2198918 A1	23-01-1997
			DE 69615993 D1	22-11-2001
			DE 69615993 T2	04-04-2002
			EP 1130188 A2	05-09-2001
			EP 1143084 A2	10-10-2001
			EP 1143085 A2	10-10-2001
			EP 0777800 A1	11-06-1997
			WO 9702395 A1	23-01-1997
			JP 10505644 T	02-06-1998
US 4454267	A	12-06-1984	AT 28207 T	15-07-1987
			AU 571473 B2	21-04-1988
			AU 2202683 A	17-07-1984
			CA 1190342 A1	09-07-1985
			DE 3372373 D1	13-08-1987
			DK 394884 A ,B,	17-08-1984
			EP 0128157 A1	19-12-1984
			ES 528149 D0	16-02-1986
			ES 8605017 A1	01-08-1986
			FI 843006 A ,B,	27-07-1984
			GB 2132185 A ,B	04-07-1984
			IE 56439 B1	31-07-1991
			JP 4080958 B	21-12-1992
			JP 60500134 T	31-01-1985
			KR 8601881 B1	24-10-1986
			MX 164897 B	30-09-1992
			NO 843291 A	17-08-1984
			NO 159730 B	24-10-1988
			NZ 206023 A	11-07-1986
			WO 8402531 A1	05-07-1984
FR 2736079	A	03-01-1997	FR 2736079 A1	03-01-1997
			AU 719427 B2	11-05-2000
			AU 6013696 A	05-02-1997
			BR 9606456 A	14-07-1998
			CA 2198918 A1	23-01-1997
			DE 69615993 D1	22-11-2001
			DE 69615993 T2	04-04-2002
			EP 1130188 A2	05-09-2001
			EP 1143084 A2	10-10-2001
			EP 1143085 A2	10-10-2001
			EP 0777800 A1	11-06-1997
			WO 9702395 A1	23-01-1997
			JP 10505644 T	02-06-1998
			US 6105325 A	22-08-2000
EP 0521804	A	07-01-1993	FR 2678652 A1	08-01-1993
			AT 160830 T	15-12-1997
			AU 1932292 A	07-01-1993
			DE 69223349 D1	15-01-1998
			DE 69223349 T2	26-03-1998
			EP 0521804 A1	07-01-1993
			FI 923055 A	03-01-1993
			HU 64120 A2	29-11-1993

INTERNATIONAL SEARCH REPORT
 information on patent family members

International Application No
 PCT/EP 01/09336

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0521804 A		NO 922597 A PL 295126 A1	04-01-1993 22-03-1993
DE 3721668 A	05-01-1989	DE 3721668 A1 AT 388550 B	05-01-1989 25-07-1989
JP 60065197 A	13-04-1985	NONE	
JP 9109131 A	28-04-1997	NONE	

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 February 2002 (14.02.2002)

PCT

(10) International Publication Number
WO 02/12144 A2

- (51) International Patent Classification⁷: C04B 26/04, E04F 13/00
- (74) Agent: CABINET HIRSCH; Groupement N° 161, 34, rue de Bassano, F-75008 Paris (FR).
- (21) International Application Number: PCT/EP01/09336
- (22) International Filing Date: 31 July 2001 (31.07.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/633,264 4 August 2000 (04.08.2000) US
- (71) Applicant (for all designated States except US): **LA-FARGE PLATRES [FR/FR]**; 500, rue Marcel Demouque, Zone du Pôle Technologique - Agroparc, F-84915 Avignon Cedex (FR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **ZUBER, François [FR/FR]**; Villa Les-Deux-Pins, Colline Saint-Anne, F-84270 Vedère (FR). **LECLERCQ, Claude [FR/FR]**; Chemin des Coudoulets, F-84800 Pernes-les-Fontaines (FR). **BOURNE-CHASTEL, Pascal [FR/FR]**; Rue Le Cours, F-84570 Mormoiron (FR). **COLBERT, Elizabeth, A. [US/US]**; 1461 Oxbow Drive, Blacklick, OH 43004 (US). **GAGNE, Pierre [CA/CA]**; 2572 Beaucourt, Varennes, Quebec J3X 1K1 (CA). **BOUCHER, Roland [CA/CA]**; 1176 Rue Girard, St-Hubert, Quebec J4T 1H4 (CA). **BILODEAU, Sylvie [CA/CA]**; 219 Chemin St-Armand, St-Armand, Quebec J0J 1T0 (CA).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declaration under Rule 4.17:**
— of inventorship (Rule 4.17(iv)) for US only
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD, ASSEMBLY AND ADDITIONAL COAT FOR THE CONSTRUCTION OF INTERIOR WORKS

WO 02/12144 A2

(57) Abstract: The present invention provides a construction assembly for interior works, comprising: prefabricated elements, preferably flat prefabricated elements e.g. gypsum fiberboards, cement fiberboards, gypsum wall boards or plaster boards, wherein said prefabricated elements comprise a coating layer formed of at least one skim coat deposited on said prefabricated elements by a coating device; and at least one jointing material, e.g. a sealing coat, joint coat and/or joint pointing coat, which joints adjacent said prefabricated elements to form a substantially plane outer surface comprising the visible surface of said at least one jointing material and the visible surface of the skim coated prefabricated elements, wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the composition of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said skim coat form, both in a dry state, a substantially homogeneous outer surface having over substantially all its surface at least one of the parameters comprised in the group consisting of color, coloration, reflectance factor and surface water absorbability which is substantially homogeneous over said surface; and whereby said outer surface is ready to be decorated. For instance, said at least one of the parameters differs by no more than 10 %, preferably at least 95 %, homogeneity is achieved.

TITLE OF THE INVENTION

METHOD, ASSEMBLY AND ADDITIONAL COAT FOR THE
CONSTRUCTION OF INTERIOR WORKS

CROSS-REFERENCE TO RELATED APPLICATIONS

This is a continuation-in-part application of U.S. Patent Application No. 09/316,013, filed May 21, 1999, which is a continuation application of U.S. Patent Application No. 08/793,444, filed May 9, 1997, the disclosure of which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to the construction of interior works. More particularly, the invention is concerned with any construction method, involving prefabricated elements, especially flat prefabricated elements such as boards, and at least one jointing material, e.g. a sealing coat, joint coat and/or a joint-pointing coat, which can be used especially for the finishing of a joint. The prefabricated elements can be gypsum fiberboards, cement fiberboards, gypsum wallboards or plaster boards comprising a plaster board and at least one sheet of lining paper, at least one outer layer of which has a visible outer face ready to be decorated. Said prefabricated elements are assembled together, optionally with a jointing material, and the joints are finished with a sealing coat, joint coat and/or joint-pointing coat, so as to obtain an overall visible outer surface which is relatively uniform or plane, including in the region of the joints. Such a method is employed, for example, when plasterboards covered with a cardboard lining having a joint-pointing coat are assembled, for the purpose of defining spaces within a building, especially partitions.

Description of Related Art

According to the document EP-A-0,521,804, the lining paper may comprise an upper layer, called an upper web, comprising white cellulose fibres, mainly synthetic, and a mineral filler of light colour, preferably white, and a pigment layer covering the upper layer, comprising a mineral filler of light colour, preferably white, and a binder.

In general the overall visible outer surface obtained according to the above-defined method needs to be prepared, before receiving any surface decoration, such as one or more layers of a film covering of the paint or lacquer type or a wallpaper. This preparation is necessitated especially by the shade or colour differences existing between the visible outer surface of the flat prefabricated elements, for example plasterboards, and the visible outer surface of the joints. After the interior work has been completed, this preparation involves covering the overall surface obtained, i.e., the lining of the flat prefabricated elements plus the joints, with one or more layers of a paint or priming or finishing coat.

The preparation operation represents an appreciable additional cost, for example in a complete process for the construction of a building. And in some cases, it is still insufficient for obtaining an overall decorated surface of uniform appearance, particularly in view of the physico-mechanical differences prevailing between the joints and the flat prefabricated elements.

Summary of the Invention

The object of the present invention is to overcome the abovementioned disadvantages. More specifically, the object of the invention is a construction method breaking with the traditional approach adopted for solving the problem explained above, that is to say avoiding the need for a preparation of the overall surface, before any decoration. However, the

object of the invention is a method which remains compatible with the practices of the professionals in the construction industry, especially those involved in interior works.

According to the present invention, the method differs from the traditional approach in that

(1) the structure and/or composition of the external surfaces of prefabricated elements, preferably flat prefabricated elements such as boards, e.g. gypsum fiberboards, cement fiberboards, cement wallboards or plasterboards comprising a sheet of lining paper and a plaster body, and

(2) the composition of a jointing material, e.g. a sealing coat, a joint coat and/or a joint-pointing coat, are coordinated with one another in order, in the dry state of the jointing material, e.g. the sealing coat, joint coat and/or joint-pointing coat, to obtain an overall surface having one or more physical characteristics, including colour or shade, which are substantially homogeneous in virtually the entire overall surface, including in the region of the visible outer face of the joints. For instance, the one or more physical characteristics differ by no more than 10%, preferably no more than 5%, at different parts of the overall surface, so that at least 90%, preferably at least 95%, homogeneity is achieved. In other words, as an example, when the jointing material is dry, the one or more physical characteristics of the outer surface of the jointing material can differ by not more than 10%, preferably not more than 5%, from the corresponding physical characteristics of the outer surface of the prefabricated elements.

According to [✓]other objects of the invention, a construction assembly for interior works is provided, comprising

(1) at least one prefabricated element, preferably a flat prefabricated element, especially a board such as a gypsum fiberboard, cement fiberboard, cement wallboard or plaster board comprising a plaster body and a lining paper, wherein at least one outer layer of which has a visible outer face ready to be decorated, and

(2) a jointing material, e.g. a sealing coat, joint coat and/or joint-pointing coat capable of being used especially for the finishing of a joint.

In this assembly, the structure and/or composition of the external surface of the prefabricated element, e.g. the sheet of lining paper of the plaster board, and the composition of the jointing material, e.g. a sealing coat, joint coat and/or joint-pointing coat, are coordinated with one another in order, in the dry state of the joint material, to obtain an overall surface having one or more physical characteristics, including colour or shade, which are substantially homogeneous in virtually the entire overall surface, including in the region of the visible outer face of the joints (for instance, the one or more physical characteristics differ by no more than 10%, preferably no more than 5%, at different parts of the overall surface, so that at least 90%, preferably at least 95%, homogeneity is achieved on the overall surface based on the one or more physical characteristics).

In the present invention, the final joint between adjacent prefabricated elements can be made of a sealing coat or joint coat as a primary joint, with the application of a joint-pointing coat as a secondary or finishing joint. Alternatively, in the present invention, the final joint between adjacent prefabricated elements can be made of the sealing coat or joint coat finished with one or more further layers of the same sealing or joint coat.

A joint-pointing coat, intended to be used in the method or the assembly according to the invention, is also provided.

The present invention affords the following decisive advantages which result from the surface homogeneity of the overall surface obtained according to the present invention, not only in terms of color or shade, but also in terms of particular physical or physico-chemical characteristics.

Thus, by homogenizing the surface absorption capacity of the lining paper and of the jointing material, e.g. the sealing coat, joint coat and/or joint-pointing coat, a virtually perfect appearance of the paint layer or paint layers and a virtually uniform adhesion of a wallpaper can be obtained. This subsequently is conducive to the homogeneous detachment of the wallpaper.

Description of the Preferred Embodiments

In a preferred version of the invention, there is a sealing coat intended for forming essentially the joints between various flat prefabricated elements, with the joint-pointing coat being a finishing coat which can be applied to the sealing coat.

According to the advantageous embodiment of the invention, when there are preexisting flat prefabricated elements, the composition of the jointing material, e.g. the sealing coat, joint coat and/or the joint-pointing coat, is coordinated with the structure and/or composition of the outer surface of the flat prefabricated elements, e.g. the sheet of lining paper.

According to another version of the invention, and converse to the foregoing, for a preexisting joint-pointing coat, the composition of the outer surface of the flat prefabricated

elements, e.g. the sheet of lining paper, is coordinated with the composition of the jointing material, e.g. the sealing coat, joint coat and/or the joint-pointing coat.

Moreover, the method is more preferably characterized in that, in addition to the colour or shade, at least any one of the following physical characteristics is homogenized or matched between flat prefabricated elements and the jointing material, namely:

- the surface appearance, including reflectance;
- the absorption of surface water;
- decoloration or coloration under the effect of natural light.

Advantageously, these various physical characteristics are defined as follows:

- the reflectance factor of the overall surface, including that of the visible outer face of the joints, is between 70% and 80%, and preferably between 72% and 76%, for a wavelength of 457 nm;
- the decoloration or coloration of the overall surface, including that of the visible outer face of the joints, has a colour deviation (ΔE^*) at most equal to 3 after exposure for 72 hours to a source of UV radiation arranged at 15 cm from the surface and having a wavelength at least equal to 290 nm;
- the surface water absorption of the overall surface, including that of the visible outer face of the joints, is not less than 60 minutes and/or is at most equal to 15 g/m² according to the COBB test, at 23°C.

In practice, and by means of routine tests, the average person skilled in the art knows how to coordinate the structure and/or composition of the outer surface, e.g. the sheet of lining paper, of the prefabricated elements such as boards, and/or the composition of the

externally visible jointing material, e.g. the joint-pointing coat, so as to satisfy the above-defined technical principles. As a result, the examples described below are in no way limiting.

The present invention will now be described by taking flat prefabricated elements, plasterboards, as an example. These boards are typically composed of a factory-cast plaster body between two sheets of paper forming both its lining and its reinforcement.

Conventionally, one of the sheets of paper used for making the plasterboards has a dark colour which can vary between a grey colour and a chestnut colour, since it is composed of cellulose fibres which have not undergone any particular purifying treatment. Traditionally, this so-called grey paper is obtained from unbleached chemical pulp and/or from mechanical pulp, and/or from thermomechanical pulp and/or from semi-chemical pulp. By mechanical pulp, it is usually meant a pulp obtained entirely by mechanical means from various raw materials, essentially wood, which can be provided by salvaged products originating from wood, such as old cardboard boxes, trimmings of kraft paper and/or old newspapers. Thermomechanical pulp means a pulp obtained by thermal treatment followed by a mechanical treatment of the raw material. By semi-chemical pulp is meant a pulp obtained by eliminating some of the non-cellulose components from the raw material by means of chemical treatment and requiring a subsequent mechanical treatment in order to disperse the fibres.

The other sheet of plasterboards has a visible face, called a lining face, of a colour generally lighter than the grey sheet. To obtain this lighter colour, the layer or layers of this face are based on chemical pulp, if appropriately bleached, composed of recycled and/or new cellulose fibres, and/or on mechanical pulp, if appropriately bleached. By chemical pulp is meant a pulp obtained by eliminating a very large proportion of the non-cellulose components

from the raw material by chemical treatment, for example, by cooking in the presence of suitable chemical agents, such as soda or bisulphites. When this chemical treatment is completed by bleaching, a large part of the coloured substances is eliminated, as well as the substances which risk decomposing by ageing and giving unpleasant yellow shades associated with the presence of, for example, lignin.

In a preferred embodiment of the method of the invention, according to the document EP-A-0 521 804, the content of which is incorporated by reference, the lining paper comprises an upper layer, called an upper web, comprising white cellulose fibres, mainly synthetic, a mineral filler of light colour, preferably white, and a pigment layer covering the upper layer. The pigment layer comprises a mineral filler of light colour, preferably white, and a binder. Correspondingly, according to the present invention, the joint-pointing coat comprises a mineral filler of light colour, preferably white, the grain size of which is between 5 and 35 μm .

The fineness of the grain size of the mineral filler of the joint-pointing coat makes it possible to obtain a smooth surface corresponding to that of the lining of the board. Too large a grain size of the filler gives rise to overall surface defects, such as a reflection of light radiation on the surface of the coat which is different from that on the surface of the board, bringing about differences in tone and brightness of the shade. Too large a grain size also gives rise to differences in physical appearance which are associated with the differences in roughness between the board and the coat.

The mineral filler represents preferably between 50% and 85% of the total weight of the joint-pointing coat.

Moreover, the coat can comprise a hydrophobic agent, for example between 0.2% and 5%, and preferably between 0.5% and 3%, of the total weight of the coat, for example a silicone derivative. This agent slows the drying kinetics of the coat, which is conducive to the non-cracking of the coat. Also, this agent has higher resistance to the attack of steam during operations for the removal of wallpaper, so that the removal can be achieved without thereby impairing the good bonding of a paint or paper adhesive on the overall surface, including the visible surface of the joints. In fact, this hydrophobic agent makes it possible to level off the absorbent capacities of the surfaces of the coat and of the lining paper of the board. Thus, all paints or paper adhesives applied to the overall surface obtained exhibit little shift in absorption kinetics between the coat and the board, thus making it possible to avoid the appearance of spectra or of defects in shade homogeneity.

The coat also comprises an organic binder dispersible in aqueous phase, in a proportion of between 1 and 20%, and preferably between 2 and 12%, of the total weight of the joint-pointing coat, for example polyvinyl acetates and/or acrylic acid esters. The choice of this binder is important, since it must impart sufficient flexibility to the coat to withstand mechanical stresses, and it must have both an adhesive capacity for obtaining a good bond on the overall surface and good resistance to the attacks of UV light.

Moreover, a handling agent is provided in the composition of the coat, especially a water-retaining and thickening agent, for example methylhydroxyethylcellulose, in a proportion of 1 to 15%, and preferably of 2 to 12%, of the total weight of the joint-pointing coat.

Finally, at least one slipping agent can be included in the composition of the coat, especially a clay, in the proportion of 0.1 to 2%, and preferably of 0.1 to 0.6%, of the total

weight of the joint-pointing coat. These clays are preferably silicate derivatives and more preferably clays of the attapulgite type.

Other components, such as biocides, dispersants, anti-foaming agents and pigments can also be incorporated in the composition of the coat in the conventional way.

The invention will be understood better from the following detailed example given as a non-limiting indication.

We proceed from plasterboards similar to Example 5 of document EP-A-0 521 804, which are assembled by means of a conventional sealing joint, for example a joint coat sold under the registered trade mark of "PREGYLYS"® of the Company PLATRES LAFARGE. The upper web of the lining of the board is obtained from 65% bleached synthetic cellulose fibres and 35% talcum and is covered with a pigment layer comprising, as mineral filler, 85% by weight of $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$ in the form of needles of a length of between 3 and 5 μm and, as a binder, 10.3% by weight of styrene-butadiene copolymer. The sealing joint subsequently receives a thin layer of a joint-pointing coat according to the invention, having the following composition:

- 50 to 85% by weight of calcium carbonate, grain size from 5 to 35 μm , as a mineral filler;
- 2 to 12% by weight of a binder comprising polyvinyl acetates and acrylic acid esters in aqueous dispersion;
- 0.5 to 3% by weight of a silicone derivative as a hydrophobic agent;
- 0.1 to 0.9% of a cellulose derivative of the methylhydroxyethylcellulose type;
- 0.1 to 0.6% of a slipping agent of the attapulgite type;
- 1 to 12% of another silicate derivative as an additional slipping agent;
- 0.1 to 5% of a polycarboxylic acid ammonium salt as a dispersant;

- 0.001 to 0.015 of an iron oxide as a pigment;
- 0.1 to 0.3% of a preparation of N-formoles and isothiazolinones as a biocide;
- 0.1 to 0.3% of a conventional anti-foaming agent;
- water up to 100%.

The weight percentages given are in relation to the total weight of the coat, unless indicated otherwise.

For comparison requirements, standard boards conforming solely to French standard NF P 72-302 and not comprising the above-defined upper web and pigment layer are assembled by means of a joint coat for a plasterboard of the range of coats "PREGYLYS"®, sold by the Company PLATRES LAFARGE.

The characteristics of the two overall surfaces thus formed are compared by applying the following tests:

(A) Degree of whiteness or reflectance factor R obtained according to standard NFQ 03038 with a wavelength of 457 nm. This degree represents the percentage ratio between of a reflected radiation of the body in question and that of a perfect diffuser under the same conditions.

(B) Surface water absorption obtained, for example, according to the COBB test. In this test, a ring defining an area of 100 cm² is filled with distilled water at 23 °C to a height of approximately 10 mm. The water is left in contact with the overall surface forming the bottom of the ring for one minute, and then the water is emptied and the excess spin-dried. The weight gain of the surface is subsequently determined and brought back to an area of 1 m². In an alternative version, a drop of distilled water of a volume of approximately 0.05 cm³ at 23 °C is deposited on

the surface. It is important that the drop be deposited and not allowed to fall from a variable height which consequently would crush it to a greater or lesser extent, thus falsifying the result. The duration in minutes represents the surface absorption of the tested area.

(C) UV radiation resistance obtained by exposing the overall surfaces, in a cabinet comprising eight high pressure mercury vapour lamps, each of 400 watts, to a wavelength which is not less than 290 nm. The surfaces are maintained at a distance of 15 cm from the lamps and at a temperature of 60°C for 72 hours. The colour deviations ΔE^* are measured on a spectrophotometer according to the standard DIN 6174 at an angle of 8°, illuminant D65 as a bright specular, included in the system L^* , a^* , b^* , in which L^* is the luminance, a^* represents the transition from green to red, and b^* represents the transition from blue to yellow. A point E^* in this system, the said point being a function of L^* , a^* , b^* , defines the colorimetry of a sample and the deviation is measured in relation to a reference point. In general terms, a colour deviation beyond 2 becomes discernible to the naked eye.

The results of the tests (A) and (B) are collated in Table I and those of the test (C) are collated in Table II below.

Table I

	Standard overall surface	Overall surface according to the invention
Reflectance R (%)	Board: 50 to 60 Coat: 65 to 85	Board: 72 to 76 Coat: 72 to 76

13

Absorption	19	13
COBB (g/m ²)	Board: 50	Board: ≥ 60
Alternative (min)	Coat: 15	Coat: ≥ 60

This shows that the overall surface according to the present invention is clearly more homogeneous than that of an assembly according to the conventional technique. Moreover, the more homogeneous absorption time of the overall surface makes it possible to use a paint having less covering capacity than that necessary with traditional boards and coats and is also beneficial to the painting operation.

Table II

Before Exposure	Standard	Invention
Initial measurements of the board	L* = 82.94 a* = -0.43 b* = 4.64	L* = 90.41 a* = -0.03 b* = 3.13
Initial measurements of the joint	L* = 90.70 a* = 0.73 b* = 5.28	L* = 89.70 a* = 0.50 b* = 3.60
	Board/Joint colour deviation delta E* = 7.87	Board/Joint colour deviation delta E* = 1
Exposure to UV for 72 hours		
Measurements of the board after exposure	L* = 81.10 a* = 0.69 b* = 12.93	L* = 90.38 a* = -0.91 b* = 7.40
	Colour deviation delta E* = 8.56; very substantial yellowing plus chestnut spots	Colour deviation delta E* = 4.36; substantial yellowing
Measurements of the joint after exposure	L* = 88.90 a* = 0.91 b* = 3.83	L* = 89.17 a* = 0.50 b* = 3.19
	Colour deviation delta E* = 2.32; slight yellowing plus a few chestnut spots	Colour deviation delta E* = 0.67; very slight colour deviation

This table shows that the colour deviation before exposure to UV is much slighter for an overall surface according to the invention than for an overall surface such as is obtained traditionally.

This table also shows that the change in the colour deviation after exposure to UV is much less pronounced in the overall surface according to the invention than traditionally. In

fact, the colour deviation before exposure and after exposure must be as little as possible, so that the overall surface does not give the impression to the naked eye of being spotted or being covered with zones of different shade and brightness.

This is not possible with an overall surface obtained by means of traditional plasterboards and products, but the very slight deviation of the overall surface according to the invention makes it possible to mitigate this disadvantage.

The present invention also provides in an alternate embodiment another way to provide a good matching at the joints between the prefabricated elements, preferably flat prefabricated elements such as gypsum fiberboards, cement fiberboards, gypsum wallboards or plaster boards.

According to this embodiment, a coat having a composition similar and/or adapted to the composition of the jointing material, e.g. the sealing coat, joint coat and/or the joint-pointing coat, is applied as a so-called "skim coat" (*i.e.*, a film coat of relatively low thickness) on the outer surface of the prefabricated elements, e.g. the liner of standard plaster boards. This skim coat is applied, for example in the plant by, for instance, roll coating or spraying via a coating device, on the prefabricated element so that the skim-coated prefabricated element is delivered to the assembly site already with a skim coat on it. Said skim coat, since it has a composition matching the composition of the jointing material, e.g. the sealing coat, joint coat and/or the joint-pointing coat, for a joint will provide, once applied, uniform characteristics to the final surface.

The invention thus provides a construction assembly for interior works, comprising:

prefabricated elements, preferably flat prefabricated elements e.g. gypsum fiberboards, cement fiberboards, gypsum wall boards or plaster boards, wherein

said prefabricated elements comprise a coating layer formed of at least one skim coat deposited on said prefabricated elements by a coating device; and at least one jointing material, e.g. a sealing coat, joint coat and/or joint pointing coat, which joints adjacent said prefabricated elements to form a substantially plane outer surface comprising the visible surface of said at least one jointing material and the visible surface of the skim coated prefabricated elements, wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the composition of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said skim coat form, both in a dry state, a substantially homogeneous outer surface having over substantially all its surface at least one of the parameters comprised in the group consisting of coloration, reflectance factor and surface water absorbability which is substantially homogeneous over said surface; and whereby said outer surface is ready to be decorated. For instance, said at least one of the parameters differs by no more than 10%, preferably no more than 5%, at different parts of the overall surface, so that at least 90%, preferably at least 95%, homogeneity is achieved. In other words, as an example, when said at least one jointing material and the prefabricated elements are dry, said at least one of the parameters of the visible surface of said at least one jointing material can differ by not more than 10%, preferably not more than 5%, from the corresponding parameter of the visible surface of the prefabricated elements.

In the present invention, the prefabricated elements, preferably flat, can be gypsum fiberboards, cement fiberboards, gypsum wallboards or plaster boards. In this embodiment, the prefabricated elements preferably are plaster boards, each of which plaster

boards comprises a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers of a color, preferably white, and/or a mineral filler of a color, preferably a light color.

According to a preferred embodiment, said at least one jointing material and said at least one skim coat exhibit substantially the same surface water absorbability. Preferably, said at least one jointing material and said at least one skim coat exhibit also substantially the same coloration and/or reflectance factor.

According to a preferred embodiment, said at least one jointing material, e.g. the joint-pointing coat, and said at least one skim coat have substantially the same solids formulation, the skim coat when applied having a solids content lower than the jointing material when applied.

Especially, when the skim coat is applied, the viscosity will be adjusted to the viscosity needed for the coating apparatus that will be used.

The coating apparatus is generally a coating roll, which is operated under standard conditions for coating a product onto a board. The dimensions, rotation speed, feeding, temperature, and any other operating conditions are within the skill of a person of ordinary skill in the art.

For example, compared to the jointing material such as the joint-pointing coat, the skim coat, when applied (for example, when the skim coat is applied to the prefabricated elements, or when the skim coated prefabricated elements are assembled in the methods of the present invention), will comprise more water than initially present in the jointing material such as the joint-pointing coat. It will thus generally comprise additional water, e.g., about 10 to 60%.

preferably about 15 to 40%, more preferably about 25%, more water than initially present in the jointing material such as the joint-pointing coat. By "water initially present in the jointing material", it means the amount of water present in the jointing material when the jointing material is applied to the skim coated prefabricated elements, before the jointing material is in a dry state.

The final thickness of the skim coat (determined when dry) is generally between about 0.001 and about 3 mm, preferably between about 0.01 and about 2 mm, more preferably between about 0.01 and about 1 mm, and most preferably between about 0.2 and about 1 mm.

According to another preferred embodiment, the jointing material such as the sealing coat, joint coat and/or joint-pointing coat and the skim coat have the following composition, by weight:

- 40 to 70% of a mineral filler, such as calcium carbonate;
- 1 to 10% of hydrophobic surface perlite;
- 0.1 to 10% of a binder such as polyvinyl acetates and acrylic acid esters in aqueous solution;
- 0.1 to 10% of a handling agent such as a cellulosic ether;
- 0.1 to 5% of a slipping agent such as clay;
- 0.1 to 20% of another silicate derivative as an additional slipping agent, such as talc and mica;
- water with optional conventional additives up to 100%.

The compositions of the jointing material such as the joint-pointing coat and the skim coat are not limited to the components disclosed above in the above amounts for the

preferred embodiment. These components may be present in other amounts in the compositions of the jointing material such as the joint-pointing coat and the skim coat.

By using the embodiment involving the skim coat, it is possible to obtain the same surface water absorption, reflectance factor and/or colour deviation as with the first embodiment depicted above, i.e. the embodiment involving adapting the composition of the jointing material, e.g. the sealing coat, joint coat and/or joint-pointing coat, to the composition of the surface of the prefabricated elements, e.g. the upper layer or web and/or the pigment layer of the plaster boards, to form a substantially homogeneous outer surface in the dry state.

The invention also provides a method for the construction on interior works, comprising the following steps:

assembling, with at least one jointing material, e.g. a sealing coat, joint coat and/or joint-pointing coat, prefabricated elements (preferably flat prefabricated elements such as gypsum fiberboards, cement fiberboards, gypsum wallboards or plaster boards, each of which plaster boards comprises a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers of a color, preferably white, and/or a mineral filler of a color, preferably a light color), wherein said prefabricated elements have a coating layer formed of at least one skim coat deposited on an outer surface of said prefabricated elements by a coating device;

jointing between adjacent said prefabricated elements with a sealing coat or joint coat to form at least one joint;

finishing said at least one joint with at least one jointing material, wherein said at least one jointing material can be a sealing coat, joint coat and/or joint pointing coat; and thereafter
drying said at least one jointing material;

wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the compositions of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said at least one skim coat form, both in a dry state, a substantially homogeneous outer surface having over substantially all its surface at least one parameter (which parameter can be a parameter selected from the group consisting of coloration, reflectance factor and surface water absorbability) which is substantially homogeneous over said surface; and whereby said outer surface is ready to be decorated. For instance, said at least one parameter differs by no more than 10%, preferably no more than 5%, at different parts of the overall surface, so that at least 90%, preferably at least 95%, homogeneity is achieved. In other words, as an example, when the at least one jointing material and the prefabricated elements are dry, said at least one parameter of the visible surface of the at least one jointing material can differ by not more than 10%, preferably not more than 5%, from the corresponding parameter of the visible surface of the prefabricated elements.

The invention also provides a kit for the construction of interior works,
comprising:

at least one prefabricated element, preferably a flat prefabricated element such as a board, e.g. a gypsum fiberboard, cement fiberboard, gypsum wallboard or

plaster board (said plaster board comprising a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers of a color, preferably white, and/or a mineral filler of a color, preferably a light color), wherein said prefabricated element comprises a coating layer formed of at least one skim coat deposited on an outer surface of said prefabricated element by a coating device;

at least one jointing material, e.g. a sealing coat, joint coat and/or joint-pointing coat, for jointing said prefabricated elements to form a substantially plane outer surface comprising the visible surface of at least one joint and the visible surface of the skim-coated prefabricated element,

wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the compositions of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said at least one skim coat form, both in a dry state, a substantially homogeneous outer surface having over substantially all its surface at least one parameter (which one parameter can be a parameter selected from the group consisting of coloration, reflectance factor and surface water absorbability) which is substantially homogeneous over said surface; and whereby said outer surface is ready to be decorated. For instance, said at least one parameter differs by no more than 10%, preferably no more than 5%, at different parts of the overall surface, so that at least 90%, preferably at least 95%, homogeneity is achieved. In other words, as an example, when the at least one jointing material and the prefabricated elements are dry, said at least one parameter of the visible surface of the at least one jointing material can differ by not more than

10%, preferably not more than 5%, from the corresponding parameter of the visible surface of the prefabricated elements.

Finally, the invention provides a plaster board useful for carrying out the method of the invention, as well as other methods for the construction on interior works, where said
5 plaster board is a flat prefabricated plaster board, comprising a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers of a color, preferably white, and/or a mineral filler of a color, preferably a light color, and a coating layer formed of at least one skim coat deposited on said lining paper by a coating roll, the at least one skim coat having a thickness generally between about
10 0.001 and about 3 mm, preferably about 0.01 and about 2 mm, more preferably between about 0.1 and about 2 mm, and most preferably between about 0.2 and about 1 mm.

The invention applies equally to fiberboards and cementboards.

Also, according to one embodiment, the difference of color between the visible face of said at least one jointing material and the visible face of said at least one skim coat form,
15 both in a dry state, expressed as ΔE^* is at most equal to about 2.

CLAIMS

1. A construction assembly for interior works, comprising:

(1) skim coated prefabricated elements comprising prefabricated elements having at
5 least one skim coat deposited on said prefabricated elements;

(2) at least one jointing material jointing said skim coated prefabricated elements to
form a substantially plane outer surface comprising a visible surface of at least one joint and
a visible surface of the skim coated prefabricated elements,

wherein said at least one jointing material and said at least one skim coat comprise a
10 mineral filler, a binder and water; and wherein the compositions of said at least one jointing
material and said at least one skim coat are adapted to each other, whereby said at least one
jointing material and said at least one skim coat form, both in a dry state, a substantially
homogeneous outer surface having, over substantially an entire visible surface of said at least
one jointing material and substantially an entire visible surface of said at least one skim coat,
15 at least one parameter selected from the group consisting of color, coloration, reflectance
factor and surface water absorbability that is substantially homogeneous over said outer
surface; and whereby said outer surface is ready to be decorated.

2. The construction assembly according to claim 1, wherein said at least one
20 jointing material and said at least one skim coat exhibit substantially the same surface water
absorbability.

3. The construction assembly according to claim 1 or 2, wherein said at least one

jointing material and said at least one skim coat have substantially the same solids formulation, said at least one skim coat when applied having a solids content lower than said at least one jointing material when applied.

5 4. The construction assembly according to claim 3, wherein said at least one skim coat comprises about 15 to 40% more water than initially present in said at least one jointing material, preferably about 25%.

 5. The construction assembly according to any one of claims 1 to 4, wherein said
10 at least one skim coat is applied to said prefabricated elements with a coating roll.

 6. The construction assembly according to any one of claims 1 to 5, wherein said at least one skim coat has a thickness between about 0.01 mm and about 2 mm, preferably between about 0.2 and about 1 mm.

15

 7. The construction assembly according to any one of claims 1 to 6, wherein said at least one jointing material is at least a joint-pointing coat, wherein said joint-pointing coat and said at least one skim coat have the following composition by weight:

 40 to 70% of a mineral filler;
20 1 to 10% of hydrophobic surface perlite;
 0.1 to 10% of abinder;
 0.1 to 10% of a handling agent;
 0.1 to 5% of a slipping agent;

0.1 to 20% of another silicate derivative as an additional slipping agent;
and water with optional conventional additives up to 100%.

8. The construction assembly according to claim 7, wherein the mineral filler is
5 calcium carbonate, the binder is either polyvinyl acetate or acrylic acid ester in aqueous
solution, the handling agent is a cellulosic ether, the slipping agent is clay, and the additional
slipping agent is either talc or mica.

9. The construction assembly according to any one of claims 1 to 8, wherein the
10 surface water absorption of the overall surface, including that of a visible face of said at least
one jointing material in a dry state, is not less than 60 minutes and/or is at most equal to 15
g/m² according to the COBB test, at 23°C.

10. The construction assembly according to any one of claims 1 to 9, wherein the
15 reflectance factor of the overall surface, including that of a visible face of said at least one
jointing material in a dry state, is in the range of 70% to 80% for a wavelength of 475 nm,
preferably in the range of 72% to 76%.

11. The construction assembly according to any one of claims 1 to 10, wherein the
20 discoloration or coloration of the overall surface, including that of a visible face of said at
least one jointing material in a dry state, has a color deviation (ΔE^*) at most equal to 3
after exposure for 72 hours to a source of UV radiation arranged at 15 cm from the surface
and having a wavelength at least equal to 290 nm.

12. The construction assembly of any one of claims 1 to 11, wherein said prefabricated elements are plaster boards, each of which plaster boards comprising a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer
5 or web comprising cellulose fibers and/or a mineral filler.

13. The construction assembly of claim 12, wherein the cellulose fibers are white and the mineral filler is of a light color.

10 14. The construction assembly of any one of claims 1 to 11, wherein said prefabricated elements are fiber plaster boards, each of which plaster boards comprising a plaster body with fibers, where the outer surfaces are free of paper.

15 15. The construction assembly of claim 14, wherein said plaster boards comprise an outer surface free of fibers.

16. The construction assembly of any one of claims 1 to 11, wherein said prefabricated elements are cement fiberboards.

20 17. The construction assembly of any one of claims 1 to 16, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 10% at different parts of the outer surface, so that at least 90% homogeneity is achieved.

18. The construction assembly of claim 17, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 5% at different parts of the outer surface, so that at least
5 95% homogeneity is achieved.

19. A method for the construction of interior works, comprising the following steps:

(1) assembling skim coated prefabricated elements, wherein said skim coated
10 prefabricated elements have a coating layer formed of at least one skim coat deposited on said prefabricated elements by a coating device;

(2) jointing adjacent prefabricated elements with at least a sealing coat or joint coat to form joints;

(3) finishing said joints between adjacent said prefabricated elements with at least
15 one jointing material, wherein said at least one jointing material is a sealing coat, joint coat or joint-pointing coat; and thereafter

(4) drying said at least one jointing material;

wherein said at least one jointing material and said at least one skim coat comprise a mineral filler, a binder and water; and wherein the composition of said at least one jointing
20 material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said at least one skim coat form, both in a dry state, a substantially homogeneous outer surface having, over substantially an entire visible surface of said at least one jointing material and substantially an entire visible surface of said at least one skim coat,

at least one parameter selected from the group consisting of color, coloration, reflectance factor and surface water absorbability that is substantially homogeneous over said outer surface; and whereby said outer surface is ready to be decorated.

5 20. The method according to claim 19, wherein said at least one jointing material and said at least one skim coat exhibit substantially the same surface water absorbability.

 21. The method assembly according to claim 19 or 20, wherein said at least one jointing material and said at least one skim coat have substantially the same solids
10 formulation, said at least one skim coat when applied having a solids content lower than said at least one jointing material when applied.

 22. The method according to claim 21, wherein said at least one skim coat comprises about 15 to 40% more water than initially present in said at least one jointing
15 material, preferably about 25%.

 23. The method assembly according to any one of claims 19 to 22, wherein said at least one skim coat is applied to said prefabricated elements with a coating roll.

20 24. The method assembly according to any one of claims 19 to 23, wherein said at least one skim coat has a thickness between about 0.01 mm and about 2 mm, preferably between about 0.2 and about 1 mm.

25. The method assembly according to any one of claims 19 to 24, wherein said at least one jointing material is at least a joint-pointing coat, wherein said joint-pointing coat and said at least one skim coat have the following composition by weight:

40 to 70% of a mineral filler;

5 1 to 10% of hydrophobic surface perlite;

0.1 to 10% of a binder;

0.1 to 10% of a handling agent;

0.1 to 5% of a slipping agent;

0.1 to 20% of another silicate derivative as an additional slipping agent;

10 and water with optional conventional additives up to 100%.

26. The method according to claim 25, wherein the mineral filler is calcium carbonate, the binder is either polyvinyl acetate or acrylic acid ester in aqueous solution, the handling agent is a cellulosic ether, the slipping agent is clay, and the additional slipping
15 agent is either talc or mica.

27. The method according to any one of claims 19 to 26, wherein the surface water absorption of the overall surface, including that of a visible face of said at least one jointing material in a dry state, is not less than 60 minutes and/or is at most equal to 15 g/m²
20 according to the COBB test, at 23°C.

28. The method according to any one of claims 19 to 27, wherein the reflectance factor of the overall surface, including that of a visible face of said at least one jointing

material in a dry state, is in the range of 70% to 80% for a wavelength of 475 nm, preferably in the range of 72% to 76%.

29. The method according to any one of claims 19 to 28, wherein the discoloration
5 or coloration of the overall surface, including that of a visible face of said at least one
jointing material in a dry state, has a color deviation (ΔE^*) at most equal to 3 after
exposure for 72 hours to a source of UV radiation arranged at 15 cm from the surface and
having a wavelength at least equal to 290 nm.

10 30. The method of any one of claims 19 to 29, wherein said prefabricated
elements are plaster boards, each of which plaster boards comprising a plaster body and at
least one sheet of lining paper, wherein the lining paper comprises an upper layer or web
comprising cellulose fibers and/or a mineral filler.

15 31. The method of claim 30, wherein the cellulose fibers are white and the mineral
filler is of a light color.

32. The method of any one of claims 19 to 29, wherein said prefabricated
elements are fiber plaster boards, each of which plaster boards comprising a plaster body
20 with fibers, where the outer surfaces are free of paper.

33. The method of claim 32, wherein said plaster boards comprise an outer surface
free of fibers.

34. The method of any one of claims 19 to 29, wherein said prefabricated elements are cement fiberboards.

5 35. The method of any one of claims 19 to 34, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 10% at different parts of the outer surface, so that at least 90% homogeneity is achieved.

10 36. The method of claim 35, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 5% at different parts of the outer surface, so that at least 95% homogeneity is achieved.

15 37. A kit for the construction of interior works, comprising:

(1) at least one skim coated prefabricated element, comprising at least one prefabricated element having a coating layer formed of at least one skim coat deposited on said at least one prefabricated element by a coating device; and

(2) at least one jointing material for jointing said skim coated prefabricated
20 element to form a substantially plane outer surface comprising a visible surface of said at least one jointing material and a visible surface of said at least one skim coated prefabricated element,

wherein said at least one jointing material and said at least one skim coat comprise a

mineral filler, a binder and water; and wherein the composition of said at least one jointing material and said at least one skim coat are adapted to each other, whereby said at least one jointing material and said at least one skim coat form, both in a dry state, a substantially homogeneous outer surface having, over substantially an entire visible surface of said at least one jointing material and substantially an entire visible surface of said at least one skim coat, at least one parameter, selected from the group consisting of color, coloration, reflectance factor and surface water absorbability that is substantially homogeneous over said outer surface; and whereby said outer surface is ready to be decorated.

10 38. The kit according to claim 38, wherein said at least one jointing material and said at least one skim coat exhibit substantially the same surface water absorbability.

 39. The kit according to claim 37 or 38, wherein said at least one jointing material and said at least one skim coat have substantially the same solids formulation, said at least one skim coat when applied having a solids content lower than said at least one jointing material when applied.

 40. The kit according to claim 39, wherein said at least one skim coat comprises about 15 to 40% more water than initially present in said at least one jointing material, preferably about 25%.

 41. The kit according to any one of claims 37 to 40, wherein said at least one skim coat is applied to said prefabricated elements with a coating roll.

42. The kit according to any one of claims 37 to 41, wherein said at least one skim coat has a thickness between about 0.01 mm and about 2 mm, preferably between about 0.2 and about 1 mm.

5

43. The kit according to any one of claims 37 to 42, wherein said at least one jointing material is at least a joint-pointing coat, wherein said joint-pointing coat and said at least one skim coat have the following composition by weight:

40 to 70% of a mineral filler;

10 1 to 10% of hydrophobic surface perlite;

0.1 to 10% of abinder;

0.1 to 10% of a handling agent;

0.1 to 5% of a slipping agent;

0.1 to 20% of another silicate derivative as an additional slipping agent;

15 and water with optional conventional additives up to 100%.

44. The kit according to claim 43, wherein the mineral filler is calcium carbonate, the binder is either polyvinyl acetate or acrylic acid ester in aqueous solution, the handling agent is a cellulosic ether, the slipping agent is clay, and the additional slipping agent is
20 either talc or mica.

45. The kit according to any one of claims 37 to 44, wherein the surface water absorption of the overall surface, including that of a visible face of said at least one jointing

material in a dry state, is not less than 60 minutes and/or is at most equal to 15 g/m² according to the COBB test, at 23°C.

46. The kit according to any one of claims 37 to 45, wherein the reflectance factor
5 of the overall surface, including that of a visible face of said at least one jointing material in a dry state, is in the range of 70% to 80% for a wavelength of 475 nm, preferably in the range of 72% to 76%.

47. The kit according to any one of claims 37 to 46, wherein the discoloration or
10 coloration of the overall surface, including that of a visible face of said at least one jointing material in a dry state, has a color deviation (ΔE^*) at most equal to 3 after exposure for 72 hours to a source of UV radiation arranged at 15 cm from the surface and having a wavelength at least equal to 290 nm.

15 48. The kit of any one of claims 37 to 47, wherein said prefabricated elements are plaster boards, each of which plaster boards comprising a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers and/or a mineral filler.

20 49. The kit of claim 48, wherein the cellulose fibers are white and the mineral filler is of a light color.

50. The kit of any one of claims 37 to 47, wherein said prefabricated elements are

fiber plaster boards, each of which plaster boards comprising a plaster body with fibers, where the outer surfaces are free of paper.

51. The kit of claim 50, wherein said plaster boards comprise an outer surface free
5 of fibers.

52. The kit of any one of claims 37 to 47, wherein said prefabricated elements are cement fiberboards.

10 53. The kit of any one of claims 37 to 52, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 10% at different parts of the outer surface, so that at least 90% homogeneity is achieved.

15 54. The kit of claim 53, wherein, when said at least one jointing material and said at least one skim coat are both in a dry state, said at least one of the parameters differs by no more than 5% at different parts of the outer surface, so that at least 95% homogeneity is achieved.

20 55. A flat prefabricated board, comprising a body, and a coating layer formed of at least one skim coat deposited by a coating roll on said body, said at least one skim coat having a thickness between about 0.01 mm and about 2 mm.

56. The board according to claim 55, wherein said at least one skim coat has a thickness between about 0.2 and about 1 mm.

57. The board according to claim 55 or 56, wherein said at least one skim coat has
5 the following composition by weight:

40 to 70% of a mineral filler;

1 to 10% of hydrophobic surface perlite;

0.1 to 10% of a binder;

0.1 to 10% of a handling agent;

10 0.1 to 5% of a slipping agent;

0.1 to 20% of another silicate derivative as an additional slipping agent;

and water with optional conventional additives up to 100%.

58. The board according to claim 57, wherein the mineral filler is calcium
15 carbonate, the binder is either polyvinyl acetate or acrylic acid ester in aqueous solution, the
handling agent is a cellulosic ether, the slipping agent is clay, and the additional slipping
agent is either talc or mica.

59. The board according to any one of claims 55 to 58, wherein the surface
20 absorption of said at least one skim coat is not less than 60 minutes and/or is at most equal to
15 g/m² according to the COBB test, at 23°C.

60. The board according to any one of claims 55 to 59, wherein the reflectance

factor of said at least one skim coat is in the range of 70% to 80%, for a wavelength of 475 nm, preferably in the range of 72% to 76%.

61. The board according to any one of claims 55 to 60, wherein the discoloration
5 or coloration of said at least one skim coat has a color deviation (ΔE^*) at most equal to 3 after exposure for 72 hours to a source of Uv radiation arranged at 15 cm from the surface and having a wavelength at least equal to 290 nm.

62. The board of any one of claims 55 to 61, wherein said prefabricated elements
10 are plaster boards, each of which plaster boards comprising a plaster body and at least one sheet of lining paper, wherein the lining paper comprises an upper layer or web comprising cellulose fibers and/or a mineral filler.

63. The board of claim 62, wherein the cellulose fibers are white and the mineral
15 filler is of a light color.

64. The board of any one of claims 55 to 61, wherein said prefabricated elements
are fiber plaster boards, each of which plaster boards comprising a plaster body with fibers,
where the outer surfaces are free of paper.

20

65. The board of claim 64, wherein said plaster boards comprise an outer surface
free of fibers.

66. The board of any one of claims 55 to 61, wherein said prefabricated elements are cement fiberboards.

67. A process for the manufacture of the board according to any one of claims 55
5 to 66, comprising the step of roll-coating a bdy with a skim coat water solution, and drying the thus-coated body.